(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date 17 January 2002 (17.01.2002)

PCT

(10) International Publication Number WO 02/05294 A1

- (51) International Patent Classification⁷: H01B 1/22, 1/24, C09D 11/00, H01G 9/20, F03G 6/00, H01L 51/20
- (21) International Application Number: PCT/GB01/02912
- (22) International Filing Date: 29 June 2001 (29.06.2001)
- (25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: 0016747.8

8 July 2000 (08.07.2000) GB

- (71) Applicant (for all designated States except US): JOHN-SON MATTHEY PUBLIC LIMITED COMPANY [GB/GB]; 2-4 Cockspur Street, Trafalgar Square, London SW1Y 5BQ (GB).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): POTTER, Robert, John [GB/GB]; 23 Tanners lane, Chalkhouse Green, South Oxfordshire RG4 9AE (GB).

- (74) Agent: WISHART, Ian, Carmichael; Johnson Matthey Technology Centre, Blounts Court, Sonning Common, Reading RG4 9NH (GB).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

1777 1 (4)

(54) Title: ELECTRICALLY CONDUCTIVE INK

(57) Abstract: The invention relates to the use of electrically conductive inks, said inks comprising electrically conductive powder and electrically conducting fibres, wherein the aspect ratio of the fibres is greater than 2:1. The inks are used to form electrically conductive layers, especially in optoelectronic devices such as solar cells. The layers have considerably reduced electrical resistance than if the electrically conductive powder were used alone.

ELECTRICALLY CONDUCTIVE INK

The present invention relates to the use of conductive inks to form electrically conductive layers, especially in optoelectronic devices.

In any form of electrical power generation device, power conversion losses due to ohmic resistance of internal conductive pathways is usually undesirable and must be kept to a minimum. In conventional solid-state solar cells that convert light energy into electrical energy, such as those based on silicon, printed tracks made e.g. from silver pastes are commonly used to carry the electrical current from the active part of the cell to the external environment. Silver or similar metals are used due to their low electrical resistance. Newer types of solar cells incorporating e.g. solid polymer electrolytes and/or dye-sensitised semi-conductor powders may or may not be able to use conducting tracks based on metal pastes depending upon the chemical environment within the cells and also upon cost considerations. There is therefore a need to develop alternative conducting track and/or electrode materials for use in these types of cells that are more chemically resistant and/or are cheaper.

Particulate materials, such as e.g. carbon, are well-established electrical conductors that have been used as track and electrode material in solar cells. WO 94/15344 discloses a conductive ink comprising carbon particulate materials. Particulate carbon has also been used as part of the counter-electrode in dye-sensitised solar cells (so called Graetzel cells), often applied to substrates in the form of a paste or as an ink. However, electrical conductivity in the carbon layer or film produced under these circumstances relies on point-to-point contact between small, frequently micro-sized, carbon particles. Thus the electrical pathway is both tortuous and very sensitive to the physical and chemical nature of the carbon particle surfaces.

It has now been found that if such particulate conductive materials, such as e.g. carbon, are partially replaced by conductive fibres in inks, the resultant conductive inks or layers produced therefrom are significantly more conductive than an equivalent volume of particulate materials.

Thus, in the first aspect the present invention provides for the use of an electrically conductive ink comprising an electrically conductive powder and electrically conductive fibres wherein the aspect ratio of the fibres is greater than 2:1, to form an electrically conductive layer.

5

The electrically conductive powder suitably comprises one or more conductive particulate materials such as carbon, nickel, tungsten and F-doped tin oxide, but is preferably carbon powder. Specific examples of carbon powder that can be used include, but are not limited to, Vulcan XC72R (Cabot Carbon Limited, Stanlow, Ellesmere Port, South Wirral, L65 4HT, UK) and TIMREX KS15 Graphite (Timcal Ltd, CH-6743, Bodio, Switzerland). The electrically conductive powder suitably has a surface area in the range from 5 to $1000 \, \mathrm{m}^2/\mathrm{g}$, preferably from 20 to $250 \, \mathrm{m}^2/\mathrm{g}$.

The electrically conductive fibres have an aspect ratio of greater than 2:1, preferably greater than 10:1. The fibres may be any electrically conductive fibres, including carbon, nickel, tungsten and F-doped tin oxide, but are preferably carbon fibres. The fibres must be chosen to ensure that they are chemically compatible with the other components. The fibres are suitably of a length of at least 1 micron, preferably greater than 1mm. The conducting fibres preferably have a thickness of not more than 100 microns, preferably not more than 50 microns. Specific examples of conductive carbon fibres that may be used in the compositions of the present invention include, but are not limited to, Toray M40B 6000 50B (Toray Industries, Japan) and Graphil 34-700 12 K (Grafil Europe, Sutherland House, Matlock Road, Coventry, CV1 4JQ, UK).

25

20

The relative ratio by weight of fibres to powder is suitably in the range from 10E-04 to 1, preferably from 0.01 to 0.5.

)

The electrically conductive layer may be a film, an electrode or an electrically conductive track. There may be a preferred orientation of the electrically conductive fibres within the layer because this may enhance conductivity in a particular direction. For example, the ink may be used to form a track wherein the majority of the fibres are oriented along the direction of the track. It is possible that this will increase conductivity in the direction of the track.

10

20

25

30

The component fibres and powders may be mixed together using the following technique. An ink is made-up by hand, eg using the proportions 28.4wt% carbon powder, 17% Disperbyk 164 surfactant (Byk, Holland) and 54.6% pine oil, followed by triple-roll milling to ensure even mixing. This 'base' ink typically has a viscosity of approximately 100 Pa. The desired weight of fibre, pre-cut to the required length, is added to the base ink with manual stirring or for instance using a paddle-stirrer. After stirring for several minutes to ensure adequate mixing, the ink is ready for use. Such mixtures are suitably converted into films or tracks by applying the mixture to a substrate surface, preferably a smooth surface, by e.g. screen-printing or some similar technique and allowing the same to dry followed by suitable firing in an air or nitrogen atmosphere between 300-500°C.

The ink used in the present invention is particularly useful for making electrodes in optoelectronic devices such as solar cells (including photovoltaic cells). For instance in a solar cell, such electrodes are used for the purpose of transporting the electrical current generated by the photo-active components away to an external circuit or the next cell in a series or parallel configuration etc. The film may also serve to protect the internals of the cell from the external environment.

In a second aspect the present invention provides a solar cell comprising an electrically conductive layer formed by the use of an electrically conductive ink according to the present invention.

In a final aspect, the present invention provides a photovoltaic cell comprising an electrically conductive layer formed by the use of an electrically conductive ink according to the present invention.

The present invention is illustrated with reference to the following Example:

EXAMPLE 1

Carbon fibres, of length 1 mm were mixed in with a 'base' carbon powder ink made as described hereinbefore, by continuously stirring with a spatula for 5 minutes.

The weight ratio of carbon fibre to ink was 1:3. The fibre-containing ink was then used to form thin films of 1 x 5cm dimension on float glass substrates by screen-printing through a nylon mesh of 150 holes per inch. A single or double-pass print was normally sufficient to produce a coherent strip approximately 100 microns thick before drying. After printing of the film, the piece was fired in an air oven at 450°C for 16 minutes in air.

The conductivity of the film was measured using a standard '4-point probe' technique using a Jandel scientific commercial instrument. This technique is widely used in industry for measuring electrical conductivities. Test samples were prepared as 1 x 5cm strips on clear float glass substrates as described previously. Electrical contact was made either end of the longer side by coating silver-paint (Agar Scientific) overlays onto the samples with an overlap of 2mm each end. One current-driving and one potential-sensing lead were then connected to each end of the strip and the conductivity read directly on a Hewlett Packard high-impedance systems meter. All tests were done at room temperature and humidity. The results of this test are shown in Table 1 below:

TABLE 1

Sample tested	Thickness of 1 x 5 cm strip	Resistance across length of
	(microns)	strip (kilo-ohms)
Carbon particulate layer ink	30-40	25.8
As above but with added	30-40	0.47
fibres		<i>i.</i>

20

10

15

These results show that the combination of a carbon powder ink with carbon fibres results in a considerable reduction in the resistance of the resultant product.

CLAIMS

10

20

30

- 1. The use of an electrically conductive ink comprising an electrically conductive powder and electrically conductive fibres wherein the aspect ratio of the fibres is greater than 2:1, to form an electrically conductive layer.
- 2. The use of an electrically conductive ink as claimed in claim 1 wherein the electrically conductive powder comprises one or more of carbon, nickel, tungsten and F-doped tin oxide.
- 3. The use of an electrically conductive ink as claimed in claim 1 wherein the electrically conductive powder is carbon powder.
- The use of an electrically conductive ink as claimed in any one preceding claims
 wherein the electrically conductive powder has a surface area in the range from 5 to 1000 m²/g.
 - 5. The use of an electrically conductive ink as claimed any one of the preceding claims wherein the electrically conducting fibres are selected from carbon, nickel, tungsten and F-doped tin oxide.
 - 6. The use of an electrically conductive ink as claimed in claim 5 wherein the electrically conducting fibres are carbon fibres.
- 7. The use of an electrically conductive ink as claimed in any one of the preceding claims wherein the electrically conductive fibres have a length of at least 1 micron.
 - 8. The use of an electrically conductive ink as claimed in any one preceding claims wherein the electrically conductive fibres have a thickness of not more than 100 microns.
 - 9. The use of an electrically conductive ink as claimed in any one of the preceding claims wherein the relative ratio by weight of electrically conductive fibres to electrically conductive powder is in the range from 10E-04 to 1.

WO 02/05294 PCT/GB01/02912

- 10. A solar cell comprising an electrically conductive layer formed by the use of an electrically conductive ink as claimed in any one of the preceding claims.
- 11. A photovoltaic cell comprising an electrically conductive layer formed by the use of an electrically conductive ink as claimed in any of claims 1-9.

5

inten al Application No PCT/GB 01/02912

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01B1/22 H01B1/24 H0169/20 F03G6/00 C09D11/00 H01L51/20 According to International Patent Classification (IPC) or to both national classification and IPC B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 H01B C09D H01G F03G H01L Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, PAJ C. DOCUMENTS CONSIDERED TO BE RELEVANT Relevant to claim No. Citation of document, with indication, where appropriate, of the relevant passages 1~9 X US 5 516 546 A (HARI SIEGFRIED ET AL) 14 May 1996 (1996-05-14) column 9, line 2 - line 38; claims 1-12 10,11 US 5 877 110 A (TRUESDALE LARRY K ET AL) 1-6 2 March 1999 (1999-03-02) column 3, line 1 -line 3; column 4, line 20 - line 23; claims 1,12,24 χ WO 97 47699 A (CABOT CORP) 1-6 18 December 1997 (1997-12-18) claims 36,40-43 Á EP 0 492 858 A (ICI PLC) 1-6 1 July 1992 (1992-07-01) example 11 Further documents are listed in the continuation of box C. Patent family members are listed in annex. Special categories of cited documents: *T* later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "A" document defining the general state of the art which is not considered to be of particular relevance *E' eartier docurrient but published on or after the International filing date "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "L' document which may throw doubts on priority datm(s) or which is cited to establish the publication date of another citation or other special reason (as specified) document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "O" document referring to an oral disclosure, use, exhibition or document published prior to the international filing date but later than the priority date claimed "&" document member of the same patent family Date of the actual completion of the international search Date of mailing of the international search report 11 October 2001 23/10/2001 Name and mailing address of the ISA Authorized officer NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016 Lehnert, A

Form PCT/ISA/210 (second sheet) (July 1992)

Intern | Application No PCT/bb 01/02912

		PC1/68 01	702912
C.(Continua	tion) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication where appropriate, of the relevant passages		Relevant to claim No.
γ	WO 98 34251 A (MAY BRONISLAV HENRY ;MONIOTTE PHILIPPE GERARD (BE); COLEMAN JAMES) 6 August 1998 (1998-08-06) page 13, line 24 - line 27		10,11
A	US 5 942 048 A (ICHINOSE HIROFUMI ET AL) 24 August 1999 (1999-08-24) column 15, line 1 - line 8; claims 1,3; examples 2-1,2-6		10,11
А	DATABASE WPI Section Ch, Week 198750 Derwent Publications Ltd., London, GB; Class A82, AN 1987-353252 XP002179923 & JP 62 257976 A (SEIKO EPSON CORP), 10 November 1987 (1987-11-10) abstract		1-9
		, , , , , , , , , , , , , , , , , , ,	
		•	
	·		

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

rmation on patent family members

Intern Lai Application No
PC1/uB 01/02912

		Tillauon on pate		IDCI 3	Ì	PC1/uB	01/02912
	document earch report	Publica dat			Patent family member(s)		Publication date
US 551	6546 A	14-0	5-1996	DE	431730	2 A1	01-12-1994
00 001	.00.10			CA	212413		26-11-1994
				EP	062643		30-11-1994
				FΙ	94240		26-11-1994
				SG	4982		15-06-1998
US 587	77110 A		 3-1999	US	570791	 Б. А	13-01-1998
03 30/	77110 A	02-0	3-1999	US	466323		05-05-1987
				AT	19251		15-05-2000
				ΑÚ	66170		03-08-1995
				AU	221779		28-01-1993
				AU	318218		25-08-1989
				AU	68965		02-04-1998
				AU	366399		15-02-1996
				BR	890529		21-08-1990
				CA	133830		07-05-1996
				CA	200564		16-06-1990
				DE	6892920		08-06-2000
				DE	6892920		02-11-2000
				DK	47708		27-09-1989
				EP	035329		07-02-1990
				EP	061938		12-10-1994
				EP	096912		05-01-2000
				FI	00450		27-09-1989
				ΪĹ	8909		24-06-1994
				IL .	10906		31-10-1996
				JΡ	1012133		12-05-1998
				ĴΡ	302469		21-03-2000
				JP	1012133		12-05-1998
				ĴΡ	250333		11-10-1990
				JP	298281	9 B2	29-11-1999
				KR	961565	8 B1	20-11-1996
				NO	30466	0 B1	25-01-1999
				MO	890716	3 A1	10-08-1989
				US	561196	54 A	18-03-1997
				US	550020	0 A	19-03-1996
				ZA	890067	79 A	29-11-1989
				AT	14186		15-09-1996
				AU		29 B2 .	27-05-1993
				AU	666609		24-01-1991
				AU	6005		16-08-1990
				AU	77032		11-01-1988
	ž.			CA	132180		07-09-1993
				DE	37518		02-10-1996
				DE	2706		24-11-1988
				DK		38 A	03-02-1988
				EP	02706		15-06-1988
				FI	8805		05-02-1988
				IL		87 A	21-06-1992
				JP	28622		03-03-1999
				JP	81994		06-08-1996 24-02-1999
				JР	28602	/O RZ	24-02-1999
					82462	Α	
				JP	82462		10.01.1000
WO 97		A 18-	12–1997	JP US	57074	32 A	13-01-1998
 WO 97	747699	A 18-	12–1997	JP US US	57074 58039	32 A 59 A	08-09-1998
 WO 97	747699	A 18-	12-1997	JP US	57074 58039 33078	32 A 59 A	

rmation on patent family members

Interr at Application No
PC7/up 01/02912

				1017 08	U1/ U2912
Patent document sted in search report		Publication date		Patent family member(s)	Publication date
WO 9747699	A		AU	3308697 A	07-01-1998
WO 3747033	••		CA	2258188 A1	18-12-1997
			CN	1227584 A	01-09-1999
			DE	69706298 D1	27-09-2001
			EP	0904327 A1	31-03-1999
			EP	0910611 A1	28-04-1999
				2000512670 T	26-09-2000
				2000512329 T	19-09-2000
			WO	9747699 A1	18-12-1997
			WO	9747692 A1	18-12-1997
			ÜS	5922118 A	13-07-1999
			US	5885335 A	23-03-1999
EP 0492858		01-07-1992	AU	658848 B2	04-05-1995
Li 0492030	••	**	ΑU	8968391 A	25-06-1992
			CA	2058104 A1	22-06-1992
			EP	0492858 A2	01-07-1992
			JP	5182512 A	23-07-1993
			NZ	240924 A	26-08-1993
			PT	99897 A	29-01-1993
			ZA	9109811 A	28-10-1992
WO 9834251	Α	06-08-1998	AU	6139298 A	25-08-1998
			WO	9834251 A1	06-08-1998
US 5942048	A	24-08-1999	JP	7321351 A	08-12-1995
			JP	2750085 B2	13-05-1998
			JP	7335921 A	22-12-1995
			JP	7321353 A	08-12-1995
			JP	8046226 A	16-02-1996
			JP	8046230 A	16-02-1996
			ΑU	695669 B2	20-08-1998
			AU	2013495 A	30-11-1995
			CN	1150338 A	21-05-199
			EP	0684652 A2	29-11-199
<u> </u>			KR	195685 B1	15-06-199
JP 62257976	Α	10-11-1987	NONE		